



Sikaflex[®]-268
THE NEW STANDARD
FOR RAIL

Sikaflex®-268

Sikaflex®-268 is the new standard for direct glazing and assembly bonding for rail vehicles. The excellent weathering and acid resistance combined with very good workability makes it the perfect product for all bonding applications in a train.



TECHNOLOGICAL BENEFITS

- Superb application properties
- Very good workability
- Wide adhesion range
- Boosterable
- Excellent weathering and thermal stability
- Very good acid resistance
- Semi-glossy finish

Technical Data

Chemical base	1-Component PUR
Color	Black
Cure mechanism	Humidity curing
Non-sag properties	Very good
Application temperature	5 - 35°C (40 - 95°F)
Skin time	60 min. approx.
Open time	40 min. approx.
Shore A-hardness	55 approx.
Tensile strength	6.0 N/mm ² approx.
Lap shear strength	4.5 N/mm ² approx.
Elongation at break	500% approx.

Our most current General Sales Conditions shall apply. Please consult the most current local Product Data Sheet prior to any use.



SIKA SERVICES AG
Tueffenwies 16
8048 Zurich
Switzerland

Contact
Phone: +41 58 436 40 40
Fax: +41 58 436 55 30
www.sika.com/transportation

BUILDING TRUST

